

8-21-00

A

PTO/SB/05 (12/97)

Please type a plus sign (+) inside this box → ☐Approved for use through 09/30/00. OMB 0651-0032  
Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number

**UTILITY  
PATENT APPLICATION  
TRANSMITTAL**

(Only for new nonprovisional applications under 37 CFR 1.53(b))

Attorney Docket No.

11920-1300

First Named Inventor or Application Identifier

Michael T. Stanhope, et al.

Title

Patterned, Flame Resistant Fabrics and Methods for Making Same

Express Mail Label No.

EL492178095US

**APPLICATION ELEMENTS**

See MPEP Chapter 600 concerning utility patent application contents

**ADDRESS TO:**Assistant Commissioner for Patents  
Box Patent Application  
Washington, DC 202311. ☒ Fee Transmittal Form (e.g., PTO/SB/17)  
(Submit an original, and a duplicate for fee processing)2. ☒ Specification [Total Pages **17**]

- Descriptive title of the Invention
- Cross References to Related Applications
- Statement Regarding Fed sponsored R&D
- Reference to Microfiche Appendix
- Background of the Invention
- Brief Summary of the Invention
- Brief Description of the Drawings (if filed)
- Detailed Description
- Claim(s)
- Abstract of the Disclosure

3. ☐ Drawing(s) (35 USC d113) [Total Sheets **0**]4. Oath or Declaration [Total Pages ☐

- a. ☐ Newly Executed (original or copy)
- b. ☐ Copy from a prior application (37 CFR 1.63(d))  
(for continuation/divisional with Box 17 completed)

**[Note Box 5 below]**

- i. ☐ **DELETION OF INVENTOR(S)**  
Signed statement attached deleting inventor(s)  
named in the prior application,  
see 37 CFR 1.63(d)(2) and 1.33(b)

5. ☐ Incorporation By Reference (useable if Box 4b is checked)  
The entire disclosure of the prior application, from which a copy of  
the oath or declaration is supplied under Box 4b, is considered as  
being part of the disclosure of the accompanying application and is  
hereby incorporated by reference therein.

6. ☐ Microfiche Computer Program (Appendix)7. Nucleotide and/or Amino Acid Sequence Submission  
(if applicable, all necessary)

- a. ☐ Computer Readable Copy
- b. ☐ Paper Copy (identical to computer copy)
- c. ☐ Statement verifying identical of above copies

**ACCOMPANYING APPLICATION PARTS**

8. ☐ Assignment Papers (cover sheet & Documents(s))
9. ☐ 37 CFR 1.373(b) Statement (when there is an assignee) ☐ Power of Attorney
10. ☐ English Translation Document (if applicable)
11. ☐ Information Disclosure Statement (IDS)/PTO-1449 ☐ Copies of IDS Citations
12. ☐ Preliminary Amendment
13. ☒ Return Receipt Postcard (MPEP 503)  
(Should be specifically itemized)
14. ☐ Small Entity Statement(s) ☐ Statement filed in prior application  
(PTO/SB/09-12) Status still proper and desired
15. ☐ Certified Copy of Priority Document(s)  
(if foreign priority is claimed)
16. ☐ Other.

\*A new statement is required to be entitled to pay small entity fees, except where one has been filed in a prior application and is being relied upon

17. If a **CONTINUING APPLICATION**, check appropriate box and supply the requisite information below and in a preliminary amendment:

☐ Continuation ☐ Divisional ☒ Continuation-in-part (CIP) of prior application No: 9/62805.  
Prior application information: Examiner John Guarriello Group / Art Unit: 1771

**18. CORRESPONDENCE ADDRESS**

Customer Number or Bar Code Label

24504

(Insert Customer No. or Attach bar code label here)



Correspondence address below

NAME

David R. Risley  
Thomas, Kayden, Horstemeyer & Risley, L.L.P.

ADDRESS

100 Galleria Parkway  
Suite 1750

CITY

Atlanta

STATE

Georgia

ZIP CODE

30339-5948

COUNTRY

U.S.A.

TELEPHONE

770-933-9500

FAX

770-951-0931

Name (Print/Type)

David R. Risley

Registration No. (Attorney/Agent)

39,345

Signature

Date

8/18/00

**Burden Hour Statement:** This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Box Patent Application, Washington, DC 20231.

08/18/00

JC903 U.S. PTO

09641830-081800

PTO

09/641830

08/18/00

TO ALL WHOM IT MAY CONCERN

Be it known that Michael T. Stanhope, residing at 1052 Somerset Drive, N.W., Atlanta, Georgia, Clyde C. Lunsford, residing at 82 Peachtree Drive, Sharpsburg, Georgia, Phillip H. Riggins, residing at 4710 Kingswood Drive, Greensboro, North Carolina have invented certain new and useful improvements in

**PATTERNED, FLAME RESISTANT FABRICS  
AND METHODS FOR MAKING SAME**

of which the following is a specification.

**EXPRESS MAIL**

I hereby certify that this correspondence is being deposited with the United States Postal Service as "Express Mail Post Office To Addressee," in an envelope addressed to: Assistant Commissioner of Patents, Washington, D.C. 20231 on

8-18-00

Express Mail No. EL 492178095US

Allison Olson

Signature

**PATTERNED, FLAME RESISTANT FABRICS  
AND METHOD FOR MAKING SAME**

**CROSS REFERENCE TO RELATED APPLICATION**

5           This application is a continuation-in-part of U.S. Patent Application Serial No. 09/062,805, filed April 20, 1998, and further claims the benefit of the filing date of U.S. Provisional Patent Application Serial No. 60/149,792, filed August 19, 1999. Both of these applications are hereby incorporated by reference into the present disclosure.

**FIELD OF THE INVENTION**

10           The present invention relates to patterned, flame resistant fabrics. More particularly, the present invention relates to flame resistant fabrics well suited for use in the construction of camouflage battle dress uniforms. In addition, the invention relates to methods for making such fabrics.

**BACKGROUND OF THE INVENTION**

15           Presently, U.S. infantry troops are issued camouflage patterned garments known as battle dress uniforms (BDUs). BDUs are used both in battle and during the execution of other tasks associated with military service. The BDUs in current use are either  
20       provided with a three or four color camouflage pattern that is printed directly onto the surface of the garment fabric. The nature of the pattern (*e.g.*, color depth), as well as the particular physical construction of the fabric (*e.g.*, fiber types), are dictated by two military specifications designated as MIL-C-44436(GL) and MIL-C-44031D. These

specifications were developed after the creation and adoption of a material presently used by the military for all BDUs known as "Nyco." This material comprises 50/50 blend of nylon and cotton. Because the specifications were written based upon the Nyco material, many of the construction characteristics identified in MIL-C-44436(GL) and MIL-C-44031D specifically pertain to this material.

Although most military personnel are issued BDUs, troops involved in specialized areas of military service are often provided with flame resistant uniforms. For example, troops that work in close proximity to flammable liquids such as pilots, combat vehicle crewmen, and fuel handlers are outfitted with garments composed of meta-aramid fibers such as NOMEX® fibers, which are manufactured by DuPont of Wilmington, Delaware.

Recently, the federal government has expressed interest in providing flame resistant BDUs to military personnel. Although personnel could be issued BDUs constructed primarily of meta-aramid fibers to obtain the desired flame resistance, the costs of providing each person with such a garment would be extremely large. In addition, the tensile and tear strengths of such a fabric would likely fall far short of the requirements of MIL-C-44436(GL) and MIL-C-44031D. Although there are known fibers that have desirable flame resistance properties as well as high tensile and tear strengths, use of such fibers is generally not considered viable for BDU construction because it is difficult to form durable patterns on many of these fibers.

From the above, it can be appreciated that it is desirable to have a patterned, flame resistant fabric which would be a suitable substitute for existing BDU materials. Furthermore, it would be desirable to have a method for making such a fabric.

### **SUMMARY OF THE INVENTION**

The present disclosure relates to patterned, flame resistant fabrics. Generally speaking, the fabrics comprise a plurality of high tenacity, flame resistant fibers, and a plurality of cellulosic fibers containing a flame retardant compound, and at least one color which is printed on the fabric to form the pattern. In a preferred embodiment, the flame resistant fibers are para-aramid fibers and the cellulosic fibers are rayon fibers.

### **DETAILED DESCRIPTION OF THE INVENTION**

The present disclosure relates to flame resistant fabrics that are well suited for use in the construction of military BDUs. Although the discussion that follows focuses on BDUs and U.S. military specifications MIL-C-44436(GL) and MIL-C-44031D, it is to be understood that the fabrics described herein could be used in various other applications, if desired. In addition, it is to be understood that, for purposes of the present disclosure, fibers identified by a named material followed by the term "fiber" are not limited to fibers composed exclusively of the named material.

As identified above, MIL-C-44436(GL) and MIL-C-44031D contain many physical property requirements for materials used to construct BDUs. In view of the aforementioned difficulties in designing a flame resistant BDU, of particular concern is fabric durability as defined by tensile (*i.e.*, breaking) strength and tear strength. Table I provides the class 1 requirements set by MIL-C-44436(GL), published July 13, 1992, and MIL-C-44031D, published December 4, 1985, and amended on September 2, 1987, both of which are hereby incorporated by reference into the present disclosure.

**TABLE I**

	<u>Fabric Property</u>	<u>Summer Weight</u> <u>(MIL-C-44436(GL))</u>	<u>Winter Weight</u> <u>(MIL-C-44031D)</u>
	Breaking strength, (pounds) min.		
5	Warp	200	200
	Filling	90	125
	Tearing strength, (pounds) min.		
	Warp	7.0	11
10	Filling	5.0	8

In an effort to obtain substantial compliance with these strength requirements, the fabric of the present invention preferably comprises a plurality of high tenacity, flame resistant fibers. Preferred for the high tenacity, flame resistant fibers are non-producer colored para-aramid fibers. Such fibers are currently available under the trademarks KEVLAR<sup>®</sup>, TECHNORA<sup>®</sup>, and TWARON<sup>®</sup> from DuPont, Teijin, and Acordis, respectively. As is known in the art, para-aramid fibers are composed of aromatic polyamide. Although meta-aramid fibers are also composed of aromatic polyamide, para-aramid fibers are preferred over meta-aramid fibers because para-aramid fibers are considerably stronger.

To reduce manufacturing costs, improve wearer comfort, and improve the printability of patterns onto the material, the fabric of the present invention further preferably comprises a plurality of cellulosic fibers. Preferred for the choice of cellulosic fibers are rayon, acetate, triacetate, and lyocell. These cellulose, although softer and less expensive than the high tenacity, flame resistant fibers, are not naturally resistant to flame. To increase the flame resistance of these fibers, one or more flame retardants are incorporated into the fibers during the manufacturing process. Effective flame retardants

include phosphorus compounds and antimony compounds. Generally speaking, cellulosic fibers which contain one or more flame retardants are given the designation "FR" which indicates a flame resistant fiber. Accordingly, the preferred flame resistant cellulosic fibers are FR rayon, FR acetate, FR triacetate, and FR lyocell. Most preferably, the flame  
5 resistant cellulosic fibers are FR rayon fibers.

Typically, the blend has a percentage composition of para-aramid fibers of at least 10% with the balance primarily comprising FR rayon fibers. Preferably, the percentage composition of the para-aramid fibers is between 10% and 60%, with approximately 40% being most preferred. Although the current military specifications require a 50/50 blend  
10 of nylon and cotton, the presently preferred blend of para-aramid and FR rayon fibers is believed to be an acceptable substitute in situations where thermal and/or flame resistance is desired. Due to this alternative construction, it will be appreciated that several of the physical construction requirements (*e.g.*, yarn weight, yarns per inch) identified in MIL-C-44436(GL) and MIL-C-44031D might not be satisfied by fabric constructed in  
15 accordance with the present disclosure. However, these differences are deemed to be secondary in importance to providing a strong, flame resistant material.

In addition to the two primary fiber components identified above, the fabric can further comprise approximately 1% to 5% by percentage composition of an anti-static fiber. Although the provision of such an anti-static fiber is not considered necessary, it  
20 may be desirable. When used, the anti-static fiber can comprise a fiber having a polyethylene-carbon core with a nylon sheath such as P140 manufactured by DuPont, or F7105C manufactured by BASF.

In keeping with MIL-C-4436(GL) and MIL-C-44031D, the fabric of the present invention preferably is arranged as a rip-stop for summer weight garments, and a twill weave for winter weight garments. By way of example, the fabric can comprise a plurality of blended yarns having warp cotton counts of 38/2 c.c. and fill cotton counts of 30/2 c.c. or 15/1 c.c., with the fabric having approximately 96 ends per inch (e.p.i.) and approximately 54 picks per inch (p.p.i.).

Tables II and III provide breaking strength and tearing strength data, respectively, for a prototype summer weight fabric constructed in accordance with the present disclosure. This fabric comprised a 60/37/3 blend of FR rayon, KEVLAR®, and anti-static fibers. The blend was dyed a base shade and printed with four different colors to form the desired camouflage pattern. Although the breaking strengths identified in Table II are not as great as those presently required by MIL-C-4446(GL), these data suggest that breaking strength values in substantial compliance with the requirements are achievable.

**TABLE II**

Breaking strength, (pounds)	
Warp	160
Filling	100

With regard to tearing strength, the prototype fabric exceeded the current requirements of MIL-C-44436(GL) as indicated in Table III.



**TABLE III**

Tearing strength, (pounds)	
Warp	9.3
Filling	6.9

5

In addition to achieving substantial compliance with the strength requirements of the military specifications, of particular concern is satisfaction of the pattern requirements established for BDUs. Preferably, the camouflage patterns are applied to the BDU fabric by first dyeing the fabric a base shade and then dye printing over the base shade with the other colors of the pattern. As mentioned above, the difficulty in dyeing (and dye printing), high tenacity, flame resistant fabrics complicates satisfaction of the pattern requirements. The reasons for this difficulty are the same as those described in relation to fabric dyeing in related U.S. Patent Application Serial No. 09/062,805, filed April 20, 1998. As identified in that application, the flame retardants contained in FR celluloseics tend to be depleted by the relatively high temperatures generally considered necessary to affix dye within flame resistant fibers such as para-aramid fibers. The depletion of these flame retardants significantly reduces the flame resistance of the cellulosic fibers and therefore reduces the flame resistance of these blends.

The inventors have discovered that, contrary to conventional beliefs, high tenacity, flame resistant fibers such as para-aramid fibers can be dyed and/or dye printed at temperatures below 100°C if particular dye-assistants are used during fabric processing. Dyeing and/or dye printing at these low temperatures avoids flame retardant depletion. It is this discovery that has led to the determination that a pattern, such as a camouflage pattern, can be formed on a flame resistant fabric by dyeing the high tenacity,

flame resistant fibers and cellulosic fibers a light base shade at a temperature below 100°C, and then printing the remaining colors of the camouflage pattern onto the blend. Processing in this manner, a strong, flame resistant BDU can be produced which substantially satisfies the pattern requirements of the military specifications identified  
5 above.

The preferred dye-assistants for dyeing the high tenacity, flame resistant fibers of the blend are selected from the group consisting of N-cyclohexylpyrrolidone, benzyl alcohol, N,N-dibutylformamide, N,N-diethylbenzamide, hexadecyltrimethyl ammonium salt, N,N-dimethylbenzamide, N,N-diethyl-m-toluamide, N-octylpyrrolidone, aryl ether,  
10 Hacomid M-8/10 (an approximately 50/50 blend of N,N-dimethylcaprylamide and N,N-dimethylcapramide), and mixtures thereof.. Most preferably, however, the dye-assistant is selected from the group consisting of aryl ether, benzyl alcohol, N,N-dibutyl formamide, N-octylpyrrolidone, and mixtures thereof.

To accomplish dyeing of the high tenacity, flame resistant fibers of the blend, a  
15 dye-assistant, a dye, and other additives if desired, typically are applied to the fabric using a one-step batch-type process. By way of example, basic, acid, or disperse dyes can be used to dye the high tenacity, flame resistant fibers. In one embodiment, a roll of fabric is loaded into a jet dyer such as a pressure jet dyeing vessel in which the fabric can be circulated through an apertured venturi contained within the vessel. The fabric first is  
20 scoured and then is dyed with the aid of the selected dye-assistant. The temperature of the dyebath normally is increased gradually from room temperature to a peak temperature below approximately 100°C. Preferably, the peak temperature is approximately 85°C.

Upon reaching the predetermined peak temperature, the dyebath temperature is maintained to allow dye to penetrate the fibers.

In another embodiment, the fabric is beam dyed in conventional manner. Although jet and beam dyeing are preferred, it is to be understood that other known atmospheric dyeing methods may be equally advantageous. Irrespective of the particular dyeing method used, there is no need to pressurize the dyebath to prevent boiling since the dyeing temperature does not reach or exceed 100°C. Therefore, all dyeing can be conducted at atmospheric pressure. Optionally, the flame resistant cellulosic fibers can be dyed in similar manner. This dyeing can be conducted prior to, simultaneously with, or subsequent to dyeing of the high tenacity, flame resistant fibers. In that the cellulosic fibers normally readily accept dye, no dye-assistent is needed to dye the fibers. By way of example, direct or reactive dyes can be used to dye the cellulosic fibers.

Once the fabric has been dyed to the desired depth of shade (typically a light green or khaki for camouflage), if at all, the fabric is printed with conventional methods. By way of example, this printing can be accomplished with rotary screen printing apparatus. As will be appreciated by persons having ordinary skill in the art, printing can be achieved with dyes, pigments, or a combination of both. Where the fabric is to be dye printed, the aforementioned dye-assistants are useful in permitting the dye to penetrate the high tenacity, flame resistant fibers. In one embodiment, this dye-assistent can be added to the print paste. Alternatively, dye printing can be facilitated with dye-assistent contained within the fibers that has not been removed (*e.g.*, if the fabric is not rinsed before printing). By way of example, basic, acid, or disperse dyes can be used to dye print the high tenacity, flame resistant fibers.

Where both the high tenacity, flame resistant fibers and the cellulosic fibers are to be dye printed, printing of the two fiber types can be accomplished simultaneously. Where dye printing of the individual high tenacity, flame resistant fibers is not desired or deemed necessary, dye-assistant is not needed. In such a case, the dye-based print paste  
5 may only penetrate the flame resistant cellulosic fibers. Suitable dyes for these fibers include direct, reactive, and vat dyes. Of these, vat dyes may be preferable in military applications due to their infrared spectral reflectance properties.

When the fabric is to be pigment printed only, dye-assistant is unnecessary in that the pigment is applied to the fabric as a surface coating instead of a fiber penetrating dye.

10 Although such pigment printing is feasible, it is presently prohibited by the military specifications identified herein and therefore not presently preferred. As mentioned above however, because these specifications may change over time, an at least partially pigment printed fabric is presently contemplated.

Once printed, the fabric then can be finished in a conventional manner. This  
15 finishing process can include the application of wicking agents, water repellents, stiffening agents, softeners, and the like. Through these techniques, it is believed that full shades of color are achievable which substantially comply with the military BDU specifications.

While preferred embodiments of the invention have been disclosed in detail in the  
20 foregoing description and drawings, it will be understood by those skilled in the art that variations and modifications thereof can be made without departing from the scope of the invention as set forth in the following claims.

**CLAIMS**

1. A patterned flame resistant fabric, comprising:  
a plurality of non-producer colored high tenacity, flame resistant fibers;  
a plurality of cellulosic fibers containing a flame retardant compound; and  
at least one color that is printed on the fabric to form said pattern.
2. The fabric of claim 1, wherein said high tenacity, flame resistant fibers are para-aramid fibers.
3. The fabric of claim 1, wherein said cellulosic fibers are selected from rayon, acetate, triacetate, and lyocell.
4. The fabric of claim 1, wherein said cellulosic fibers are rayon fibers.
5. The fabric of claim 1, wherein said fabric has a percentage composition of high tenacity, flame resistant fibers of at least 10%.
6. The fabric of claim 1, wherein said fabric has a percentage composition of high tenacity, flame resistant fibers from approximately 10% to 60%.
7. The fabric of claim 1, wherein said fabric has a percentage composition of high tenacity, flame resistant fibers of approximately 40%.

9. The fabric of claim 1, wherein said fabric contains a residual amount of dye-assistant selected from the group consisting of aryl ether, benzyl alcohol, N,N-dibutyl formamide, N-octylpyrrolidone, and mixtures thereof.

contacting the flame resistant fabric with a dye-assistant selected from the group consisting of N-cyclohexylpyrrolidone, benzyl alcohol, N,N-dibutylformamide, N,N-diethylbenzamide, hexadecyltrimethyl ammonium salt, N,N-dimethylbenzamide, N,N-diethyl-m-toluamide, N-octylpyrrolidone, aryl ether, an approximately 50/50 blend of N,N-dimethylcaprylamide and N,N-dimethylcapramide, and mixtures thereof; and

wherein the flame resistant fabric is not exposed to a temperature exceeding

13

11. The method of claim 10, wherein the high tenacity, flame resistant fibers are para-aramid fibers.

12. The method of claim 10, wherein the cellulosic fibers are selected from rayon, acetate, triacetate, and lyocell.

13. The method of claim 10, wherein the cellulosic fibers are rayon fibers.

14. The method of claim 10, wherein the fabric has a percentage composition of high tenacity, flame resistant fibers of at least 10%.

15. The method of claim 10, wherein the fabric has a percentage composition of high tenacity, flame resistant fibers from approximately 10% to 60%.

16. The method of claim 10, wherein the fabric has a percentage composition of high tenacity, flame resistant fibers of approximately 40%.

17. The method of claim 10, wherein the fabric is contacted with a dye-  
assistant selected from the group consisting of aryl ether, benzyl alcohol, N,N-dibutyl  
formamide, N-octylpyrrolidone, and mixtures thereof.

18. The method of claim 10, wherein the fabric is not exposed to a temperature exceeding 85°C.

19. The method of claim 10, wherein three different colors are printed onto the fabric.

20. The method of claim 10, wherein four different colors are printed onto the fabric.

21. The method of claim 10, wherein the fabric is printed on using a rotary screen printing apparatus.

22. The method of claim 10, further comprising dyeing the fabric a base shade prior to printing.

22. The method of claim 22, wherein dyeing is conducted at temperatures not exceeding 100°C.

23. The method of claim 22, wherein dyeing is conducted at temperatures not exceeding 85°C.

24. The method of claim 22, wherein the fabric is dyed using a jet dyer.



25. The method of claim 10, wherein the pattern comprises a camouflage pattern.

003730" 0E8T4360

## ABSTRACT

5